

# DivoEco®UD3

№	Property, unit	Value							Test standard	Tolerance
		170	215	260	290	without glue				
						320	340	410		
1	Grammage, gsm	170	215	260	290	320	340	410	DSTU 2297	±3%
2	Thickness, µm	220	290	350	395	445	470	580	DSTU EN 20534	±5%
3	Stiffness L&W (5°), mNm:								DIN 53121	±15%
	- CD	-	2,9	5,5	7,8	10,2	12,6	21,4		
	- MD	-	12,5	21,1	29,6	37,7	44,2	67,9		
4	Surface water absorption (COBB <sub>60</sub> ), gsm:								DSTU 3549 ISO 535	
	- Top;									
	- Bottom		max 50				min 100			
5	Brightness Top, %, min				46				DSTU ISO 2470-2	

Laboratory test climate: (23±1,0) °C, (50±2,0) %.

Issued: 27.11.2019.

All figures mentioned above may be subject to technical changes.

Cardboard complies with hygienic requirements of Ukrainian Legislation.

## Packaging

Sheet	width:	max 1580 mm	min 600 mm
	length:	max 1580 mm	min 490 mm
	bale height:	max 1400 mm	min 800 mm
	type of packaging:	shrink film, bale on the pallet with the busbar	

Reel	width:	max 2500 mm	min 480 mm
	diameter:	max 1400 mm	min 950 mm
	type of packaging:	paper	
	core:	76 mm, 100 mm, 150 mm	

