

DivoPack®UD1

№	Property, unit	Value						Test standard	Tolerance
		170	220	250	310	without glue			
						350	410		
1	Grammage, gsm	170	220	250	310	350	410	DSTU 2297	±3%
2	Thickness, µm	220	290	340	420	450	580	DSTU EN 20534	±5%
3	Stiffness L&W (5°), mNm:							DIN 53121	±15%
	- CD	-	3,2	4,4	9,8	14,5	22,3		
	- MD	-	13,8	18,6	34,3	50,6	73,7		
4	Surface water absorption (COBB ₆₀), gsm:							DSTU 3549 ISO 535	
	- Top;								
	- Bottom			max 50			min 100		
				max100					
5	Brightness Top, %, min				76			DSTU ISO 2470-2	

Laboratory test climate: (23±1,0) °C, (50±2,0) %.

Issued: 27.11.2019.

All figures mentioned above may be subject to technical changes.

Cardboard complies with hygienic requirements of Ukrainian Legislation.

Packaging

Sheet	width:	max 1580 mm	min 600 mm
	length:	max 1580 mm	min 490 mm
	bale height:	max 1400 mm	min 800 mm
	type of packaging:	shrink film, bale on the pallet with the busbar	

Reel	width:	max 2500 mm	min 480 mm
	diameter:	max 1400 mm	min 950 mm
	type of packaging:	paper	
	core:	76 mm, 100 mm, 150 mm	

