

## B-0 (fluting)

№	Property unit	B-0			Test standard
		112±6	125±6	140±8	
1	Burst strength, kPa, min.	260	290	340	ДСТУ ISO 2759
2	Water Absorption Top, COBB60, gsm: - Top - Back side		20-45 not less 70		ДСТУ 3549 ISO 535
3	Short Span Compressive Strength SCT, CD, kN/m, min.	1,9	2,1	2,4	ISO 9895
4	Moisture, %		6,0-8,0		ГОСТ 13525.19 ISO 287

Laboratory test climate: (23±1)°C, (50±2)%.  
 Issued: 01.08.2019.  
 All figures mentioned above may be subject to technical changes.

## Packaging

Reel	width:	max 2500 mm	min 500 mm
	diameter:	max 1400 mm	min 950 mm
	type of packaging:	paper	
	core:	150 mm	

