

KT-50

№	Property unit	KT-50	Test standard
		140±8	
1	Burst strength, H, min	340	ISO 2759
2	Water Absorption Top, COBB ₆₀ , [*] gsm: - Top, min - Back side	70 20-45	ISO 535
3	Short Span Compressive Strength SCT, CD, kN/m, min.	2.2	ISO 9895
4	Brightness Top, %, ±2	70	ISO 2470-2
5	Moisture, %	6.0-8.0	ISO 287

Laboratory test climate: (23±1)°C, (50±2)%.

Issued: 01.08.2019.

All figures mentioned above may be subject to technical changes.

Packaging

Reel	width:	max 2500 mm	min 500 mm
	diameter:	max 1400 mm	min 950 mm
	type of packaging:	paper	
	core:	150 mm	