

KTU-VP

№	Property unit	KTU-VP		Test standard
		140±8	175±10	
1	Burst strength, kPa, min.	340	380	ISO 2759
2	Short Span Compressive Strength SCT, CD, kN/m, min.	2,1	2,8	ISO 9895
3	Water Absorption Top gsm: - (COBB ₁₈₀₀) Top, max. - (COBB ₆₀) Back side, max.	100 45		ISO 535
4	Wet tensile strength - MD 15 mm 20 min, % min.	6,0		ISO 3781
5	Moisture, %	6,0-8,0		EN ISO 287

Laboratory test climate: (23±1)°C, (50±2)%.

Issued: 21.10.2019.

All figures mentioned above may be subject to technical changes.

Packaging

Reel	width:	max 2500 mm	min 500 mm
	diameter:	max 1400 mm	min 950 mm
	type of packaging:	paper	
	core:	150 mm	

