

# KTU

№	Property unit	KTU					Test standard
		112±6	125±6	140±8	175±10	200±12	
1	Burst strength, H, min	260	290	340	380	390	ISO 2759
2	Short Span Compressive Strength SCT, CD, kN/m, min.	1.7	1.9	2.2	2.9	3.2	ISO 9895
3	Water Absorption Top, COBB <sub>60</sub> , gsm: - Top, min - Back side			70 20-45			ISO 535
4	Moisture, %			6.0-8.0			ISO 287

Laboratory test climate: (23±1)°C, (50±2)%.  
 Issued: 01.08.2019.  
 All figures mentioned above may be subject to technical changes.

## Packaging

Reel	width:	max 2500 mm	min 500 mm
	diameter:	max 1400 mm	min 950 mm
	type of packaging:	paper	
	core:	150 mm	