

DivoPrint GD3

№	Property unit	Value						Test standard	Tolerance
		230	250	280	310	350	370		
1	Grammage, g/m ²	230	250	280	310	350	370	DSTU 2297	+2/-4%
2	Thickness, μm	280	310	350	400	450	480	DSTU EN 20534	+3/-7%
3	Stiffness L&W (5°), mNm:							DIN 53121	-15%
	- CD	2,7	3,7	5,3	7,8	11,2	13,6		
	- MD	8,7	11,7	17,5	24,8	33,9	40,8		
4	Brightness Top, %, (D65/2)	82						DSTU ISO 2570 ISO 2470-2	±2

Laboratory test climate: (23±1)^oC, (50±2)%.

Issued: 01.06.2021.

All figures mentioned above may be subject to technical changes.

Packaging

Sheet	width:	max 1580 mm	min 470 mm
	length:	max 1580 mm	min 520 mm
	bale height:	max 1400 mm	min 800 mm
	type of packaging:	shrink film, bale on the pallet with the busbar	

Reel	width:	max 2500 mm	min 500 mm
	diameter:	max 1400 mm	min 950 mm
	type of packaging:	paper	
	core:	150 mm	