

# GT2

№	Property, unit	Value				Test standard	Tolerance
		250	300	400	440		
1	Grammage, gsm	250	300	400	440	DSTU 2297	+2/-4%
2	Thickness, µm	300	365	505	560	DSTU EN 20534	+3/-7%
3	Stiffness L&W (5°), mNm:					DIN 53121	-15%
	- CD	3,0	6,8	18,4	22,8		
	- MD	11,5	20,4	53,4	70,4		
5	Brightness Top, %, min		86			DSTU ISO 2470-2	±2

Laboratory test climate: (23±1) °C, (50±2) %.  
 Issued: 01.06.2021.  
 All figures mentioned above may be subject to technical changes.

## Packaging

Sheet	width:	max 1580 mm	min 470 mm
	length:	max 1580 mm	min 520 mm
	bale height:	max 1400 mm	min 800 mm
	type of packaging:	shrink film, bale on the pallet with the busbar	

Reel	width:	max 2500 mm	min 500 mm
	diameter:	max 1400 mm	min 950 mm
	type of packaging:	paper	
	core:	150 mm	