

DivoBoard GDBD

№	Property, unit	Value			Test standard	Tolerance
		380	400	440		
1	Grammage, gsm	380	400	440	DSTU 2297	+2/-4%
2	Thickness, µm	490	510	580	DSTU EN 20534	+3/-7%
3	Stiffness L&W (5°), mNm: - CD - MD	15,5	19,4	25,2	DIN 53121	-15%
		43,2	54,4	68,0		
5	Brightness Top, %, min		82		DSTU ISO 2470-2	±2

Laboratory test climate: (23±1) °C, (50±2) %.
 Issued: 01.06.2021.
 All figures mentioned above may be subject to technical changes.

Packaging

Sheet	width:	max 1580 mm	min 470 mm
	length:	max 1580 mm	min 520 mm
	bale height:	max 1400 mm	min 800 mm
	type of packaging:	shrink film, bale on the pallet with the busbar	

Reel	width:	max 2500 mm	min 500 mm
	diameter:	max 1400 mm	min 950 mm
	type of packaging:	paper	
	core:	150 mm	