

# Liner GD3

№	Property unit	Value		Test standard	Tolerance
		155	180		
1	Grammage, g/m <sup>2</sup>	155	180	DSTU 2297	±3%
2	Burst strength, kPa	300	350	ISO 2759	-10%
3	Short Span Crush Test SCT, CD, kN/m	2,3	2,5	ISO 9895	-0,2%
4	Water Absorption, COBB <sub>60</sub> , back side, gsm	not more 100		DSTU 3549 ISO 535	
5	Brightness Top, %	84		IS ДСТУ 2570 ISO 2470-2	±2,0%

Laboratory test climate: (23±1)°C, (50±2)%.  
 Issued: 06.04.2021.  
 All figures mentioned above may be subject to technical changes.

## Packaging

Reel	width:	max 2500 mm	min 500 mm
	diameter:	max 1400 mm	min 950 mm
	type of packaging:	paper	
	core:	150 mm	