

DivoLux GD2

| № | Property unit | Value | | | | | | | | | Test standard | Tolerance |
|---|----------------------------|-------|------|------|------|------|------|------|------|------|-------------------------|-----------|
| | | 230 | 250 | 280 | 300 | 320 | 340 | 380 | 400 | 440 | | |
| 1 | Grammage, g/m ² | 230 | 250 | 280 | 300 | 320 | 340 | 380 | 400 | 440 | DSTU 2297 | +2/-4% |
| 2 | Thickness, μm | 275 | 305 | 345 | 380 | 405 | 435 | 480 | 515 | 580 | DSTU EN 20534 | +3/-7% |
| 3 | Stiffness L&W (5°), mNm: | | | | | | | | | | DIN 53121 | -15% |
| | - CD | 3,0 | 3,9 | 5,8 | 6,8 | 8,7 | 10,7 | 14,6 | 17,5 | 22,8 | | |
| | - MD | 10,2 | 13,6 | 18,9 | 24,3 | 28,7 | 34,0 | 48,1 | 56,3 | 68,4 | | |
| 4 | Brightness Top, %, (D65/2) | 86 | | | | | | | | | DSTU 2570 ISO 2470-2 | ±2 |

Laboratory test climate: (23±1)°C, (50±2)%.

Issued: 01.06.2021.

All figures mentioned above may be subject to technical changes.

Packaging

| | | | |
|-------|--------------------|---|------------|
| Sheet | width: | max 1580 mm | min 470 mm |
| | length: | max 1580 mm | min 520 mm |
| | bale height: | max 1400 mm | min 800 mm |
| | type of packaging: | shrink film, bale on the pallet with the busbar | |

| | | | |
|------|--------------------|-------------|------------|
| Reel | width: | max 2500 mm | min 500 mm |
| | diameter/średnica: | max 1400 mm | min 950 mm |
| | type of packaging | paper | |
| | core: | 150 mm | |