

TLW

№	Property unit	TLW			Test standard	Tolerance
		130	150	200		
1	Burst strength, kPa, min	325	375	500	ISO 2759	-20%
2	Water Absorption Top, COBB ₆₀ , - Top, min - Back side		70 20-45		ДСТУ EN ISO 535	-
3	Short Span Compressive Strength SCT, CD, kN/m, min.	1.9	2.2	2.9	ISO 9895	-10%
4	Brightness Top, %		60		ДСТУ ISO 2470	±2%
5	Moisture, %		7,0-1,0		ДСТУ EN ISO 287	-

Laboratory test climate: (23±1)°C, (50±2)%.

Issued: 22.12.2020.

All figures mentioned above may be subject to technical changes.

Packaging

Reel	width:	max 2500 mm	min 500 mm
	diameter:	max 1400 mm	min 950 mm
	type of packaging:	paper	
	core:	150 mm	