

## CORRUGATED SINGLE-BORED TU U 21.2-05509659-028-2009

Grade of cardboard	Bursting strength (abs.)	Specific tear resistance with the application of destructive force along the corrugations on the line of scoring after one double fold for 180°	Resistance on edgewise compression along the corrugations	Delamination resistance	Moisture
	MPa min.	kN/m, min.	kN/m, min.	kN/m, min.	%
<b>TU 21.2-05509659-028:2009</b>					
TK-20	-	-	1,0	0,2	6,0-12,0
TK-21	-	3	2,2	0,2	6,0-12,0
TK-22	0,4	4	3,0	0,3	6,0-12,0
TK-23	0,6	6	3,8	0,3	6,0-12,0
TK-24	0,7	7	4,6	0,3	6,0-12,0
TK-25	0,8	8	5,4	0,3	6,0-12,0
TK-26	0,9	9	6,2	0,3	6,0-12,0
TK-27	1,0	10	7,0	0,3	6,0-12,0
TK-28	1,1	11	8,5	0,3	6,0-12,0
TK-29	1,2	12	10,0	0,3	6,0-12,0
T-21	0,7	4	2,2	0,2	6,0-12,0
T-22	0,9	6	3,0	0,2	6,0-12,0
T-23	1,1	7	3,8	0,2	6,0-12,0
T-24	1,2	8	4,6	0,2	6,0-12,0
T-25	1,3	9	5,4	0,2	6,0-12,0
T-26	1,5	10	6,2	0,2	6,0-12,0