

## CORRUGATED CARDBOARD TU U 21.2-05509659-028-2009

Grade of cardboard	Bursting strength (abs.)	Specific tear resistance with the application of destructive force along the corrugations on the line of scoring after one double fold for 180°	Resistance on edgewise compression along the corrugations	Moisture
	MPa min.	kN/m, min.	kN/m, min.	%
<b>TU U 21.2-05509659-028:2009</b>				
PK-31	0,8	6	5,0	6,0-12,0
PK-32	0,9	7	6,0	6,0-12,0
PK-33	1,0	10	8,0	6,0-12,0
PK-34	1,1	12	10,0	6,0-12,0
PK-35	1,2	13	12,0	6,0-12,0
PK-31	0,8	6	5,0	6,0-12,0
PK-32	0,9	7	6,0	6,0-12,0
P-31	1,1	7	5,0	6,0-12,0
P-32	1,4	10	6,0	6,0-12,0
P-33	1,7	13	8,0	6,0-12,0
P-34	2,0	15	10,0	6,0-12,0
P-35	2,3	17	12,0	6,0-12,0
P-36	2,5	19	15,0	6,0-12,0
P-37	2,8	21	17,0	6,0-12,0