


KT-1

Description:

Testliner from brown waste paper.

Printing methods:

Offset, flexographic, digital.



№	Property unit	Assortment range							Test standard
		112	125	140	160	180	200	230	
1	Tolerance, %	+3/-10	+3/-10	+3/-10	+4/-10	+4/-12	+4/-12	+5/-12	DSTU 2297
2	Burst strength, H, not less	240	260	290	340	360	380	430	ISO 2759
3	Short Span Compressive Strength SCT, CD, kN/m, not less	1,6	1,9	2,1	2,4	2,7	3,0	3,4	ISO 9895
4	Moisture, %	6,2-7,8							DSTU GOST ISO 287
5	Water Absorption Top, gsm: - Top - Back side	20-45 not less 70							DSTU EN ISO 535