


## KT-VP

**Description:**

Moisture-resistant testliner from brown waste paper grades with colorant addition.

**Printing methods:**

Offset, flexographic, digital.



№	Property unit	Assortment range				Test standard
		140	160	180	200	
1	Tolerance, %	+5/-10	+5/-12	+5/-12	+5/-12	DSTU 2297
2	Burst strength, kPa, min	290	320	360	380	ISO 2759
3	Short Span Compressive Strength SCT, CD, kN/m, min	2,0	2,3	2,6	2,9	ISO 9895
4	Moisture, %	6,2-7,8				DSTU GOST ISO 287
5	Water Absorption Top gsm: - Top - Back side	not more 100 not more 45				DSTU EN ISO 535
6	Wet tensile strength, %	not less 6,0				DSTU ISO 3781