


TLW

Description:

Testliner from white waste paper.

Printing methods:

Offset, flexographic, digital.



№	Property unit	Assortment range			Test standard	Tolerance
		130	150	200		
1	Grammage, g/m2	130	150	200	DSTU 2297	±3,5%
2	Burst strength, kPa, min	325	375	500	DSTU ISO 2759	-20%
3	Short Span Compressive Strength SCT, CD, kN/m, min.	1,9	2,2	2,9	ISO 9895	-10%
4	Brightness Top, %	60			DSTU ISO 2470	±2
5	Moisture, %	7,0±1,0			DSTU EN ISO 287 GOST 13525.19	-
6	Water Absorption Top, gsm: - Top - Back side	20-45 not less 70		20-45 30-50	DSTU 3549	-