


DivoPack[®]UD1

Description:

Folding Box Board has top layer from bleached pulp and grey back layer.

Printing methods:

Offset, flexographic, digital.



№	Property unit	Assortment range						Test standard	Tolerance
		170	220	250	310	Without glue			
						350	410		
1	Grammage, g/m ²	170	220	250	310	350	410	DSTU 2297	±3%
2	Thickness, μm	220	290	340	420	450	580	DSTU EN 20534	±5%
3	Stiffness L&W (5°), mNm - CD - MD	- -	3,2 13,8	4,4 18,6	9,8 34,3	14,5 50,6	22,3 73,7	DIN 53121	±15%
4	Brightness Top, %	not less 76						DSTU 2570 ISO 2470-2	-
5	Moisture, %	5,0-8,0			6,0-8,5			GOST 13525.19 ISO 287	-
6	Surface water absorption gsm: - Top - Bottom	not more 50 not more 100			not less 100 not less 100			DSTU 3549 ISO 535	-